

EASY-FORM™

CLOSED CELL BACKER ROD

TRADE PACKS - CLOSED CELL FOAM ROD



EASY-FORM™ Closed Cell Backer Rod is a compressible, closed cell polyolefin foam tube with an outer skin. It is used as a backing for cold applied sealants in expansion/construction joints and building seal applications.

SEKISUI

FOAM
INTERNATIONAL
Global Foam Solutions

PHYSICALLY
CROSSLINKED
SEKISUI TECHNOLOGY

EASY-FORM™ BACKER ROD


TRADE PACKS - CLOSED CELL FOAM ROD

Profiles

- 6mm x 50m rolls
- 13mm x 50m rolls
- 10mm x 50m rolls
- 20mm x 50m rolls

Benefits

- Closed cell structure
- CFC free
- Excellent dimensional stability
- Resistant to most chemicals
- Non toxic and odourless
- No adhesion to sealants
- Rot proof
- Available in FR grades
- Available in customised shapes
- Excellent aging characteristics



Bulk Packs

Available in bulk packs with profiles from 6mm to 50mm.

Technical Specs

Test Methods: JIS-K6767

Properties	Units	Typical
Density	kg/m ³	30-37
Tensile Strength (Longitudinal)	kg/cm ²	3.3-5.8
Elongation (Longitudinal)	%	49-140
Compression Strength (Longitudinal)		
25%	kg/cm ²	0.50-0.82
50%	kg/cm ²	1.0-1.4
Compression Set (Radial)		
50% Compression	%	16-25
Water Absorption	mg/cm ²	0.4
Operating Temperature Range	°C	-80 to +80



This information on Sekisui Foam Australia foams is presented to the best of our knowledge. All product data is based on average values and is for guidance only. As these products are subject to constant research and development, we reserve the right to update the contents without notice. Date of Publication: February 2015.

Recommendations as to methods of post fabrication, application and use of Sekisui Foam Australia foams are based on our experience and knowledge of the characteristics of our products and are given in good faith. As producer of the material we have no control over the application of Sekisui Foam Australia foams and no legal responsibility is accepted for such recommendations. In particular, no responsibility is accepted by us for any system in which Sekisui Foam Australia foams are utilised or for any application. Softlon and Thermobreak - Registered trademarks of Sekisui Foam Australia.

SEKISUI

FOAM
INTERNATIONAL
Global Foam Solutions



Sekisui Foam Australia
Head Office

1-5 Parraweena Rd, PO Box 2898,
Taren Point NSW 2229 Australia
Tel: +61 2 9525 9880
Fax: +61 2 9525 8004
Email: info@sekisuifoam.com.au
Web: www.sekisuifoam.com.au

Queensland Branch

15/853 Nudgee Rd, PO Box 448,
Northgate QLD 4013 Australia
Tel: +61 7 3267 7100
Fax: +61 7 3267 7166
Email: info@sekisuifoam.com.au
Web: www.sekisuifoam.com.au