

EASY-FORM™ ***OPEN CELL BACKER ROD***

OPEN CELL POLYURETHANE FOAM ROD



EASY-FORM™ Open Cell Backer Rod is a compressible, cylindrical polyurethane foam structure that is ideal for use with One Part Sealants.

SEKISUI

FOAM
INTERNATIONAL
Global Foam Solutions


PHYSICALLY
CROSSLINKED
SEKISUI TECHNOLOGY

EASY-FORM™ OPEN CELL BACKER ROD


OPEN CELL POLYURETHANE FOAM ROD

Applications


- Vertical and horizontal joint filler
- Window glazing seals
- Sealing interior wall joints
- Panel walls
- Masonry expansion joints
- Pre-cast units
- Curtain wall construction
- Ideal for use with One Part Sealants




LOG CONSTRUCTION




WINDOW GLAZING




MASONRY EXPANSION JOINTS




DOORS




COPINGS



CURTAIN WALL CONSTRUCTION



PANEL WALLS



PRE-CAST UNITS

Technical Specs

Properties	Test Method	Unit	Typical Value
Density	JIS K6400	kg/m ³	25 (nominal)
Tensile Strength (longitudinal)	JIS K6400	kg/cm ²	>0.7
Elongation (longitudinal)	JIS K6400	%	>150
Compression Strength 25% Deflection	JIS K6400	N	150
Compression Set	JIS K6400	%	<6
Cell Size	JIS K6400	pores per inch	48 (nominal)

Roll Sizes

Diameter (mm)	Roll Length (m)	Pack Qty (rolls)
10	200	20
15	150	14
20	100	10
25	80	10
30	60	10
40	30	10
50	20	10



This information on Sekisui Foam Australia foams is presented to the best of our knowledge. All product data is based on average values and is for guidance only. As these products are subject to constant research and development, we reserve the right to update the contents without notice. Date of Publication: February 2015.

Recommendations as to methods of post fabrication, application and use of Sekisui Foam Australia foams are based on our experience and knowledge of the characteristics of our products and are given in good faith. As producer of the material we have no control over the application of Sekisui Foam Australia foams and no legal responsibility is accepted for such recommendations. In particular, no responsibility is accepted by us for any system in which Sekisui Foam Australia foams are utilised or for any application. Softlon and Thermobreak - Registered trademarks of Sekisui Foam Australia.

SEKISUI

FOAM
INTERNATIONAL
Global Foam Solutions



Sekisui Foam Australia

Head Office

1-5 Parraweena Rd, PO Box 2898,
Taren Point NSW 2229 Australia
Tel: +61 2 9525 9880
Fax: +61 2 9525 8004
Email: info@sekisuifoam.com.au
Web: www.sekisuifoam.com.au

Queensland Branch

15/853 Nudgee Rd, PO Box 448,
Northgate QLD 4013 Australia
Tel: +61 7 3267 7100
Fax: +61 7 3267 7166
Email: info@sekisuifoam.com.au
Web: www.sekisuifoam.com.au