

SEKISUI FOAM AUSTRALIA

1 – 5 Parraweena Road, Taren Point
NSW 2229 AUSTRALIA

T: +61 2 9525 9880 E: info@sekisuifoam.com.au

TECHNICAL INFORMATION

TECHNICAL DATA SHEET

G60 Pressure Sensitive Adhesive

Description:

G60 is a high performance solvent based acrylic emulsion tissue tape. It provides excellent permanent adhesion and strong initial tack at room and elevated temperatures.

Adhesive System:	Solvent based acrylic
Thickness:	0.10 mm
Carrier:	Tissue paper 13 g/m ²
Release Liner:	110 g/m ² white bleached Kraft paper PE and silicone coated both sides

Product Features:

- The acrylic-based adhesive provides strong holding power with no long-term deterioration.
- It offers excellent water and solvent resistance.
- It can be re-positioned thus allowing alignment with substrate.
- It features a heavy release liner with easy-peel properties for ease of application.

Property	Typical Value	Test Method
Initial Tack	16	J. Dow No.
Adhesion to Steel	1.4 kg / 25 mm	PSTC 3
Holding Power 1kg load on 25mm x 25mm	> 24 hours	PSTC 7
Service Temperature	-20 / +80 °C	Internal
Intermittent Temperature	+120 °C	Internal

Surface Preparation:

It is essential for pressure sensitive tapes that the surface to which the tape is applied is clean and free of grease and oil. Suitable cleaning solvents are acetone and methylated spirits.



This information on Sekisui Foam International products is presented to the best of our knowledge. All product data is based on average values and is for guidance only. As these products are subject to constant research and development, we reserve the right to update the contents without notice.

Recommendations as to methods of post fabrication, application and use of Sekisui Foam International products are based on our experience and knowledge of the characteristics of our products and are given in good faith. As producer of the material we have no control over the application of Sekisui Foam International products and no legal responsibility is accepted for such recommendations. In particular, no responsibility is accepted by us for any system in which Sekisui Foam International products are utilised or for any application.

Soflon and **Thermobreak** – Registered trademarks of Sekisui Chemical Co. Ltd or its subsidiaries.

© Sekisui Pilon Pty Ltd. Date of Publication: January 2016.