

SEKISUI FOAM AUSTRALIA

1 – 5 Parraweena Road, Taren Point
NSW 2229 AUSTRALIA
T: +61 2 9525 9880 E: info@sekisuifoam.com.au

TECHNICAL INFORMATION

TECHNICAL DATA SHEET

Easy-Form™ Caulking Foam

Description:

Easy-Form™ Caulking Foam a compressible polyurethane foam profiled into donut or strip shape with optional adhesive backing. The foam is free of heavy metals, plasticisers and CFCs.

Easy-Form™ Caulking Foam is available in either white or charcoal colour and contains no fire retardants.

Property	Typical Value	Test Method
Density	30 kg/m ³ (nominal)	AS 2282:3
Tensile Strength	>180 kPa	AS 2282:6
Elongation	>110%	AS 2282:6
Tear Strength	>400 N/m	AS 2282:7
Compression Strength	350 N @ 40% deflection	AS 2282:8
Compression Set	< 10%	AS 2282:9
Resilience	> 30%	AS 2282:11



This information on Sekisui Foam International products is presented to the best of our knowledge. All product data is based on average values and is for guidance only. As these products are subject to constant research and development, we reserve the right to update the contents without notice.



Recommendations as to methods of post fabrication, application and use of Sekisui Foam International products are based on our experience and knowledge of the characteristics of our products and are given in good faith. As producer of the material we have no control over the application of Sekisui Foam International products and no legal responsibility is accepted for such recommendations. In particular, no responsibility is accepted by us for any system in which Sekisui Foam International products are utilised or for any application.



Sofilon and Thermobreak – Registered trademarks of Sekisui Chemical Co. Ltd or its subsidiaries.

© Sekisui Pilon Pty Ltd. Date of Publication: January 2016.