

**SEKISUI FOAM AUSTRALIA**

1 – 5 Parraweena Road, Taren Point  
NSW 2229 AUSTRALIA  
T: +61 2 9525 9880 E: info@sekisuifoam.com.au

# TECHNICAL INFORMATION

## TECHNICAL DATA SHEET

### Softlon® 3000

**Description:**

Softlon® 3000 series is a closed cell, electron beam crosslinked, polyolefin foam with an outer skin. The foam is free of heavy metals, plasticisers and CFCs.

Due to the unique manufacturing process, Softlon® 3000 exhibits consistent thickness and density.

| Property                  | Typical Value  | Test Method |
|---------------------------|--|-------------|
| Density                   | 33 kg/m <sup>3</sup> (nominal)   | Internal    |
| Tensile Strength          | 4.4 kg/cm <sup>2</sup> (longitudinal)<br>2.6 kg/cm <sup>2</sup> (crosswise)          | JIS K6767   |
| Elongation                | 250% (longitudinal)<br>158% (crosswise)  | JIS K6767   |
| Tear Strength             | 2.4 kg/cm (longitudinal)<br>1.5 kg/cm (crosswise)                                    | JIS K6767   |
| Compression Strength      | 0.35 kg/cm <sup>2</sup> @ 25% deflection<br>1.00 kg/cm <sup>2</sup> @ 50% deflection | Internal    |
| Compression Set           | 6.5% @ 25% deflection<br>23.0% @ 50% deflection                                      | JIS K6767   |
| Dimensional Change Heat   | -1.45% (longitudinal)<br>-0.75% (crosswise)  | 70°C, 22h   |
| Working Temperature Range | -80 / +100 °C  | Internal    |
| Water Absorption          | 0.07 mg/cm <sup>2</sup>  | JIS K6767   |
| Water Vapour Permeability | 4.6 g/m <sup>2</sup> , 24h   | JIS Z0208   |



This information on Sekisui Foam International products is presented to the best of our knowledge. All product data is based on average values and is for guidance only. As these products are subject to constant research and development, we reserve the right to update the contents without notice.



Recommendations as to methods of post fabrication, application and use of Sekisui Foam International products are based on our experience and knowledge of the characteristics of our products and are given in good faith. As producer of the material we have no control over the application of Sekisui Foam International products and no legal responsibility is accepted for such recommendations. In particular, no responsibility is accepted by us for any system in which Sekisui Foam International products are utilised or for any application.



**Softlon and Thermobreak** – Registered trademarks of Sekisui Chemical Co. Ltd or its subsidiaries.

© Sekisui Pilon Pty Ltd. Date of Publication: January 2016.